

Magnesium Alloy

Standard Magnesium Alloy (AM60)

1. CHEMICAL ANALYSIS

Chemical Analysis		Maximum
Mg	(%)	Balance
Be	(%)	0,0005 - 0,0015
Al	(%)	5,60 - 6,40
Cu	(%)	Max. 0,008
Ca	(%)	Max. 0,010
Zn	(%)	Max. 0,200
Mn	(%)	0,26 - 0,50
Ni	(%)	Max. 0,002
Fe	(%)	Max. 0,005
Si	(%)	Max. 0,080
Sn	(%)	Max. 0,010
Zr	(%)	Max. 0,010
Pb	(%)	Max. 0,010
Ti	(%)	Max. 0,010
P	(%)	Max. 0,010

* X-Ray Fluorescence

2. INGOT SIZE

Ingot (12kg) :

Length = 637 mm, Width = 139 mm, Height = 95 mm

Ingot (8kg) :

Length = 637 mm, Width = 139 mm, Height = 70 mm

3. PACKAGING

Magnesium ingots with magnesium pallet and covered by shrink-wrap

The information presented above is based on average values, and is given for guidance only.

Esan Eczacıbaşı Endüstriyel Hammaddeler Sanayi ve Ticaret A.Ş.

Istanbul Deri Organize Sanayi Bölgesi Kazlı Çeşme Cad. No:35 Orhanlı, Tuzla 34956, İstanbul / TURKEY

Tel : + 90 216 581 64 00 Faks : + 90 216 581 64 99

e-mail: esan.satis@eczacibasi.com.tr

esan.sales@eczacibasi.com.tr

www.esan.com.tr